

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
24 July 2003 (24.07.2003)


PCT

(10) International Publication Number
WO 03/060251 A1

- (51) International Patent Classification⁷: E04C 1/39, B28B 7/00
- (21) International Application Number: PCT/US02/41543
- (22) International Filing Date:
27 December 2002 (27.12.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
10/038,639 4 January 2002 (04.01.2002) US
- (71) Applicant: ANCHOR WALL SYSTEMS, INC.
[US/US]; 5959 Baker Road, Suite 390, Minnetonka, MN 55345-5996 (US).
- (72) Inventors: SCHERER, Ronald J.; 5703 Peller Avenue North, Oak Park Heights, MN 55082 (US). LACROIX, David, Matthew; 4608 103rd Lane N.E., Circle Pines, MN 55014 (US). BOLLES, Glenn, Clarke; 4708 Annaway Drive, Edina, MN 55345 (US).
- (74) Agent: BRUESS, Steven C.; Merchant & Gould, P.C., P.O. Box 2903, Minneapolis, MN 55402-0903 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GI, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PI, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GI, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report

[Continued on next page]

(54) Title: MASONRY BLOCK AND METHOD OF MAKING SAME



(57) Abstract: Molds and processes that permit high-speed, mass production of retaining wall blocks having patterned or other processed front faces, as well as retaining wall blocks formed by such processes. The invention permits the front face (12) of the block (10) to be impressed with a pattern or otherwise directly processed, to allow the formation of pre-determined block front faces, while at the same time facilitating high-speed, high-volume production of blocks (10). Pre-determined front faces (12) can include front faces (12) having pre-determined patterns and textures, front faces (12) having pre-determined shapes, front faces (12) made from different material(s) than the remainder of the block (10), and combinations thereof.

WO 03/060251 A1



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

MASONRY BLOCK AND METHOD OF MAKING SAME

This application is being filed as a PCT international patent application in the name of Anchor Wall Systems, Inc., on 27 December 2002, designating all countries except the U.S.

5

Field of the Invention

The invention relates generally to concrete masonry blocks and the manufacture thereof. More specifically, the invention relates to concrete masonry blocks suitable for use in landscaping applications, such as retaining walls, and manufacturing processes useful in the production of such blocks.

10

Background of the Invention

Modern, high speed, automated concrete block plants and concrete paver plants make use of molds that are open at the top and bottom. These molds are mounted in machines which cyclically station a pallet below the mold to close the bottom of the mold, deliver dry cast concrete into the mold through the open top of the mold, densify and compact the concrete by a combination of vibration and pressure, and strip the mold by a relative vertical movement of the mold and the pallet.

Due to the nature of such plants and the equipment used to perform this process, it is difficult to impart a natural appearance to the face of a concrete block, particularly if the block needs to include other features, such as converging side walls, and an integral locator/shear flange(s) formed on the top and/or bottom face of the block. U.S. Patent No. 5,827,015, which is incorporated herein by reference, discloses such a concrete masonry block suitable for use as a retaining wall block, and the common method for producing such a unit in a high speed, automated concrete block plant.

There is demand for a pre-formed concrete masonry unit, particularly a retaining wall block with converging side walls and/or an integral locator/shear flange formed on the top and/or bottom face, and having a more natural appearing face than is achievable by the splitting process described in U.S. Patent No. 5,827,015, or by the splitting process described in U.S. Patent No. 6,321,740, which is also incorporated herein by reference. In particular, there is a demand for

processes and tooling that will create such blocks with such faces in high-speed, automated fashion on the type of equipment commonly available in a concrete block or concrete paver plant.

Summary of the Invention

5 The invention relates to molds and processes that permit high speed, mass production of concrete masonry units, and, in particular, retaining wall blocks. These molds and processes can be used to create relatively simple decorative front faces on such blocks, similar to the split faces described in U.S. Patent No. 5,827,015. These molds and processes can also be used to create more complex
10 front faces on such blocks, similar to the split and distressed faces produced by conventional tumbling or hammermill processing, or by the process described in U.S. Patent No. 6,321,740. These molds and processes can also be used to create unique blocks that have heretofore not been available: retaining wall blocks with converging side walls and/or integral locator/shear flanges and with front faces with
15 significantly more complex faces, including faces with significant detail and relief not heretofore available in dry cast concrete block technology.

 In a preferred embodiment, the resulting blocks have patterned front faces that simulate natural stone, as well as upper and lower faces, a rear face, opposed converging side faces, and a flange extending below the lower face. Blocks
20 having this construction, when stacked in multiple courses with other similarly constructed retaining wall blocks, permits construction of serpentine or curved retaining walls that appear to have been constructed with naturally-occurring, rather than man-made, materials.

 One aspect of this invention is that a mold made in accordance with
25 the invention is arranged so that the portion of the block that will be the front face when the block is laid is facing the open top of the mold cavity during the molding process. This orientation permits the front face of the block to be formed by the action of a patterned pressure plate ("stripper shoe") in a high-speed, masonry block or paver plant. The stripper shoe can be provided with a very simple pattern, a
30 moderately complex pattern, or a highly detailed, three-dimensional pattern with significant relief, simulating naturally occurring stone. Molding the block in this orientation also makes the block face readily accessible for other processing to affect

the appearance of the face, including the application of specially-selected aggregate and/or color pigments to the face.

Another aspect of this invention is that a side wall of the mold has an undercut portion adjacent the open bottom of the mold cavity. This undercut portion
5 cooperates with the pallet that is positioned under the mold to form a subcavity of the mold. In a preferred embodiment, this subcavity forms the locator/shear flange on the surface of the block that will be the bottom of the block as laid.

Another aspect of this invention is that at least one of the side walls of the mold is angled from vertical, to form a side wall of the block as laid that
10 includes a portion that converges toward the opposite side wall as it gets closer to the rear face of the block. This angled mold side wall is moveable, so that it moves into a first position to permit the mold to be filled with dry cast concrete and the concrete to be compacted and densified, and moves into a second position to permit the densified concrete to be stripped from the mold without interference from this
15 mold side wall. In a preferred embodiment, the opposed mold side wall is similarly moveable, so that at least portions of the opposed side walls of the resulting block converge towards each other as they approach the rear of the block.

These and various other advantages and features of novelty which characterize the invention are pointed out with particularity in the claims annexed
20 hereto and forming a part hereof. However, for a better understanding of the invention, its advantages and objects obtained by its use, reference should be made to the drawings which form a further part hereof, and to the accompanying description, in which there is described a preferred embodiment of the invention.

Brief Description of the Drawings

25 Figure 1 is a perspective view of a retaining wall block according to the present invention, with the block being oriented in the position in which it is formed in the mold.

Figure 2 is a bottom plan view of the retaining wall block of Figure 1.

Figure 3 is a side elevation view of the retaining wall block of Figure
30 1.

Figure 3A is a detailed view of the portion of the retaining wall block contained within the dashed circle in Figure 3.

Figure 4 is a front view of a portion of a retaining wall constructed from a plurality of blocks according to the present invention.

Figure 5 is a flow chart illustrating the process of the present invention.

5 Figure 6 is a perspective view of a mold assembly having a plurality of mold cavities for forming a plurality of retaining wall blocks of the present invention utilizing the process of the present invention.

Figure 7 is a top plan view of the mold assembly of Figure 6.

10 Figure 8 is an end view of the mold assembly illustrating one mold cavity with opposed, converging, pivoted side walls.

Figure 9 is a schematic representation of the side walls that form the upper and lower block faces, the stripper shoe, and the pallet of the mold assembly.

Figure 10 is a perspective view of a representative pattern on the face of a stripper shoe.

15 Figure 11 is a schematic illustration of the temperature control for the stripper shoe.

Figures 12A, 12B and 12C are photographs of retaining wall blocks according to the present invention.

20 Detailed Description of the Preferred Embodiment

Overview

The present invention provides a process for producing a concrete masonry block, as well as a block resulting from the process, and a mold and mold components used to implement the process, in which a pre-determined three-
25 dimensional pattern is impressed into the face of the block, and the front face of the block can be otherwise directly processed or worked so that a pre-determined block front face can be produced in a standard dry cast concrete block or paver machine. Direct processing or working of the front face includes molding, shaping, patterning, impressing, material layering, combinations thereof, and other processes in which
30 the texture, shape, color, appearance, or physical properties of the front face can be directly affected. Further, the process can be implemented using multiple-cavity molds to permit high-speed, high-volume production of the masonry blocks on standard dry cast concrete block or paver equipment. Moreover, use of the inventive process and equipment eliminates the need for a splitting station, and/or a

hammermill station, and/or a tumbling station, and the additional equipment and processing costs associated with such additional processing stations.

The blocks produced by the process of the present invention can have a configuration that allows construction of walls, including serpentine or curved retaining walls, by stacking a plurality of blocks, having the same or different pre-determined front faces, in multiple courses, with an automatic set-back and shear resistance between courses.

The preferred embodiment will be described in relation to the impressing of a pre-determined, three-dimensional, rock-like pattern into the front face of a retaining wall block. As a result, the block, and a wall that is constructed from a plurality of the blocks when stacked into courses, appears to have been constructed with "natural" materials. The process described herein could also be used to construct masonry blocks that are used in the construction of building walls, as well as for concrete bricks, slabs and pavers.

Masonry Block

A masonry block 10 according to the present invention is illustrated in Figures 1-3. The block 10 comprises a block body having a front face 12, a rear face 14, an upper face 16, a lower face 18, and opposed side faces 20, 22. The block 10 is formed from a cured, dry cast, no slump masonry concrete. Dry cast, no slump masonry concrete is well known in the art of retaining wall blocks.

The front face 12, as shown in Figures 1-3, is provided with a pre-determined three-dimensional pattern. The pattern on the front face 12 is preferably imparted to the front face during molding of the block 10 by the action of a moveable stripper shoe (to be later described) having a pattern that is the mirror image of the front face of the block. Figures 12A-C are photos of blocks according to the present invention having patterned front faces.

The pattern that is imparted to the front face 12 can vary depending upon the desired appearance of the front face. Preferably, the pattern simulates natural stone so that the front face 12 appears to be a natural material, rather than a man-made material. The particular stone pattern that is used will be selected based on what is thought to be visually pleasing to users of the blocks. By way of example, the face of the block can be impressed with a pattern that appears to be a single stone, such a river rock. Or the block can be impressed with a pattern that

appears to be multiple river rocks in a mortared together pattern. Or the block can be impressed with a pattern that simulates a single piece of quarry rubble, or multiple pieces of field stone, stacked in layers. Endless possibilities are available. By providing stripper shoes with a variety of different patterns, the resulting patterns on the blocks can be varied by changing stripper shoes.

The resulting detail and relief that can be provided on the front face is greater than that which can be provided on a front face of a block that results from conventional splitting techniques, and the tumbling, hammermilling and other distressing techniques previously described. The relief on the patterned front face 12, measured from the lowest point to the highest point, is preferably at least 0.5 inches, and more preferably at least 1.0 inches.

In the preferred embodiment, the front face 12 lies generally in approximately a single plane between the side faces 20, 22, as opposed to the common, three-faceted and curved faces that are frequently seen in split-face retaining wall blocks, although such multi-faceted and curved faces can be easily produced with the present invention. As shown in Figure 3, the front face 12 is provided with a slight rearward slant, i.e. inclined at an angle α from the bottom lower face 18 to the upper face 16. Preferably, α is about 10 degrees. As a result, front and rear faces 12, 14 are separated by a distance d_1 adjacent the lower face 18 and by a distance d_2 adjacent the upper face 16, with d_1 being larger than d_2 . In the preferred embodiment, d_1 is about 7.625 inches and d_2 is about 6.875 inches. The width d_3 is preferably about 12.0 inches. It is also contemplated that the front face 12 between the side faces 20, 22 can be faceted, curved, or combinations thereof. In these embodiments, the front face would also have a slight rearward slant.

Typically, when retaining wall blocks are stacked into set-back courses to form a wall, a portion of the upper face of each block in the lower course is visible between the front face of each block in the lower course and the front face of each block in the adjacent upper course. The visible portions of the upper faces creates the appearance of a ledge. And, in the case of dry cast masonry blocks, this ledge typically has an artificial appearance. By providing a rearward incline angle to the front face 12 of the block 10, the appearance of the ledge can be reduced or eliminated, thus enhancing the "natural" appearance of the resulting wall.

The front face 12 also includes radiused edges 24a, 24b at its junctures with the side faces. The radiused edges 24a, 24b are formed by arcuate

flanges provided on the stripper shoe. The radius of the edges 24a, 24b is preferably about 0.25 inches. The radiused edges 24a, 24b shift the contact points between the sides of the block 10 with adjacent blocks in the same course, when a plurality of blocks are laid side-by-side, away from the front face 12, and result in better contact
5 between the blocks to prevent soil "leakage" between adjacent blocks. If desired, the top and bottom edges at the junctures between the front face 12 and the upper and lower faces 16, 18 could also be radiused, similar to the radiused edges 24a, 24b, by the provision of arcuate flanges on the stripper shoe.

With reference to Figures 1-3, the rear face 14 of the block 10 is
10 illustrated as being generally planar between the side faces 20, 22 and generally perpendicular to the upper and lower faces 16, 18. However, it is contemplated that the rear face 14 could deviate from planar, such as by being provided with one or more notches or provided with one or more concavities, while still being within the scope of the invention. The width d_4 of the rear face 14 is preferably about 8.202
15 inches.

Further, the upper face 16 is illustrated in Figures 1-3 as being generally planar, and free of cores intersecting the upper face 16. When a plurality of blocks 10 are stacked into courses to form a wall structure, the upper face 16 of each block is in a generally parallel relationship to the upper faces 16 of the other
20 blocks.

The lower face 18 of the block 10 is formed so as to be suitable for engaging the upper face 16 of the block(s) in the course below to maintain the generally parallel relationship between the upper faces of the blocks 10 when the blocks are stacked into courses. In the preferred embodiment, as illustrated in
25 Figures 1-3, the lower face 18 is generally planar and horizontal so that it is generally parallel to the upper face 16. However, other lower faces can be used, including a lower face that includes one or more concave portions or one or more channels over portions of the lower face 18. The distance d_6 between the upper face 16 and the lower face 18 is preferably about 4.0 inches.

30 In the preferred block 10, the side faces 20, 22 are generally vertical and join the upper and lower faces 16, 18 and join the front and rear faces 12, 14, as seen in Figures 1-3. At least a portion of each side face 20, 22 converges toward the opposite side face as the side faces extend toward the rear face 14. Preferably the entire length of each side face 20, 22 converges starting from adjacent the front face

18, with the side faces 20, 22 being generally planar between the front and rear faces 12, 14. However, it is possible that the side faces 20, 22 could start converging from a location spaced from the front face 12, in which case the side faces 20, 22 would comprise a combination of straight, non-converging sections extending from the front face and converging sections leading from the straight sections to the rear face 14. The converging portion of each side face 20,22 preferably converges at an angle β of about 14.5 degrees.

Alternatively, the block 10 can be provided with only one converging side face or side face portion, with the other side face being substantially perpendicular to the front and rear faces 12, 14. A block with at least one converging side face permits serpentine retaining walls to be constructed.

The block 10 also preferably includes a flange 26 that extends below the lower face 18 of the block, as seen in Figures 1-3. The flange 26 is designed to abut against the rear face of a block in the course below the block 10 to provide a pre-determined set-back from the course below and provide course-to-course shear strength.

With reference to Figure 3A, it is seen that the flange 26 includes a front surface 28 that engages the rear face of the block(s) in the course below. The flange 26 also includes a bottom surface 30, a front, bottom edge 32 between the front surface 28 and the bottom surface 30 that is arcuate, and a rear surface 34 that is extension of, and forms a portion of, the rear face 14 of the block. The front surface 28 is preferably angled at an angle γ of about 18 degrees. The angled front surface 28 and the arcuate edge 32 result from corresponding shaped portions of the mold, which construction facilitates filling of the mold with dry cast masonry concrete and release of the flange 26 from the mold.

As shown in Figures 1 and 2, the flange 26 extends the entire distance between the side faces 20, 22. However, the flange need not extend the entire distance. For example, the flange could extend only a portion of the distance between the side faces, and be spaced from the side faces. Alternatively, two or more flange portions separated from each other by a gap could be used.

With reference to Figure 3A, the depth d_f of the flange 26 is preferably about 0.750 inches. This depth defines the resulting set-back of the block relative to the course below. Other flange dimensions could be used, depending

upon the amount of desired set-back. The rear surface 34 preferably has a height d_8 of about 0.375 inches.

The concepts described can also be applied to masonry blocks that are used in the construction of building walls, as well as to concrete bricks, slabs and pavers. In these cases, it is contemplated and within the scope of the invention that neither side face of the block or brick would converge, and that the flange would not be present. However, the patterned front face would provide the block or brick a decorative appearance.

10 Block Structures

The masonry block 10 of the present invention may be used to build any number of landscape structures. An example of a structure that may be constructed with blocks according to the invention is illustrated in Figure 4. As illustrated, a retaining wall 40 composed of individual courses 42a-c of blocks can be constructed. The blocks used in constructing the wall 40 can comprise blocks having identically patterned front faces, or a mixture of blocks with different, but compatibly-patterned faces. The height of the wall 40 will depend upon the number of courses that are used. The construction of retaining walls is well known in the art. A description of a suitable process for constructing the wall 40 is disclosed in U.S. Patent 5,827,015.

As discussed above, the flange 26 on the block 10 provides set-back of the block from the course below. As a result, the course 42b is set-back from the course 42a, and the course 42c is set-back from the course 42b. Further, as discussed above, the rearward incline of the front face 12 reduces the ledge that is formed between each adjacent course, by reducing the amount of the upper face portion of each block in the lower course that is visible between the front face of each block in the lower course and the front face of each block in the adjacent upper course.

The retaining wall 40 illustrated in Figure 4 is straight. However, the preferred block 10 construction with the angled side faces 20, 22 permits the construction of serpentine or curved retaining walls, such as that disclosed in U.S. Patent 5,827,015.

Block Forming Process

An additional aspect of the invention concerns the process for forming the block 10. With reference to Figure 5, an outline of the process is shown. Generally, the process is initiated by mixing the dry cast masonry concrete that will form the block 10. Dry cast, no slump masonry concrete is well known in the art of retaining wall blocks. The concrete will be chosen so as to satisfy pre-determined strength, water absorption, density, shrinkage, and related criteria for the block so that the block will perform adequately for its intended use. A person having ordinary skill in the art would be able to readily select a material constituency that satisfies the desired block criteria. Further, the procedures and equipment for mixing the constituents of the dry cast masonry concrete are well known in the art.

Once the concrete is mixed, it is transported to a hopper, which holds the concrete near the mold. As discussed below, the mold assembly 50 includes at least one block-forming cavity 56 suitable for forming the preferred block. The cavity 56 is open at its top and bottom. When it is desired to form a block, a pallet is positioned beneath the mold so as to close the bottom of the cavity 56. The appropriate amount of dry cast concrete from the hopper is then loaded, via one or more feed drawers, into the block-forming cavity through the open top of the cavity 56. The process and equipment for transporting dry cast masonry concrete and loading a block-forming cavity are well known in the art.

The dry cast masonry concrete in the cavity 56 must next be compacted to densify it. This is accomplished primarily through vibration of the dry cast masonry concrete, in combination with the application of pressure exerted on the mass of dry cast masonry concrete from above. The vibration can be exerted by vibration of the pallet underlying the mold (table vibration), or by vibration of the mold box (mold vibration), or by a combination of both actions. The pressure is exerted by a compression head, discussed below, that carries one or more stripper shoes that contact the mass of dry cast masonry concrete from above. The timing and sequencing of the vibration and compression is variable, and depends upon the characteristics of the dry cast masonry concrete used and the desired results. The selection and application of the appropriate sequencing, timing, and types of vibrational forces, is within the ordinary skill in the art. Generally, these forces contribute to fully filling the cavity 56, so that there are not undesired voids in the

finished block, and to densifying the dry cast masonry concrete so that the finished block will have the desired weight, density, and performance characteristics.

Pressure is exerted by a stripper shoe 94 that is brought down into contact with the top of the dry cast masonry concrete in the cavity 56 to compact the concrete. The stripper shoe 94 acts with the vibration to compact the concrete within the cavity 56 to form a solid, contiguous, pre-cured block. In the preferred embodiment, the stripper shoe also includes a three-dimensional pattern 96 on its face for producing a corresponding pattern on the resulting pre-cured block as the stripper shoe compacts the concrete. Preferably, the portion of the pre-cured block contacted by the patterned shoe face comprises the front face of the block.

After densification, the pre-cured block is discharged from the cavity. Preferably, discharge occurs by lowering the pallet 82 relative to the mold assembly, while further lowering the stripper shoe 94 through the mold cavity to assist in stripping the pre-cured block from the cavity. The stripper shoe is then raised upwardly out of the mold cavity and the mold is ready to repeat this production cycle.

If the block is to have one or more converging side walls, then corresponding mold side walls, as described in detail below, must be provided in the mold. Such mold side walls must be adapted to move into a first position to permit filling of the mold, and compaction and densification of the dry cast masonry concrete, and must be adapted to move into a second position to permit stripping of the mold without damage to the pre-cured block.

Once the pre-cured block has been completely removed from the cavity, it can be transported away from the mold assembly for subsequent curing. The block may be cured through any means known to those of skill in the art. Examples of curing processes that are suitable for practicing the invention include air curing, autoclaving, and steam curing. Any of these processes for curing the block may be implemented by those of skill in the art.

Once cured, the blocks can be packaged for storage and subsequent shipment to a jobsite, and can then be used with other cured blocks in forming a structure, such as the retaining wall 40 in Figure 5.

Mold Assembly

The mold assembly 50 according to the present invention that is used to practice the invention is illustrated in Figures 6-10. The mold assembly 50 is made from materials that are able to withstand the pressure that is applied during formation of the pre-cured block, as well as provide sufficient wear life.

The mold assembly 50 is constructed so that the pre-cured block is formed with its front face facing upward, and with its rear face supported on the pallet 82 positioned underneath the mold assembly 50. This permits pattern impressing or other direct processing to occur on the front face 12 of the block, to allow the formation of pre-determined block front faces. Pre-determined front faces can include front faces having pre-determined patterns and textures, front faces having pre-determined shapes, front faces made from different material(s) than the remainder of the block, and combinations thereof.

Further, the mold assembly 50 is designed so that a pre-cured block, including a block with a lower lip or flange and/or one or more converging side faces, can be discharged through the bottom of the mold assembly.

Referring to Figure 6, the mold assembly 50 comprises a mold 52 and a compression head assembly 54 that interacts with the mold 52 as described below. The mold 52 comprises at least one block-forming cavity 56 defined therein. In one preferred embodiment, the mold 52 is sized for use in a standard, "three-at-a-time" American block machine, having a standard pallet size of approximately 18.5 inches by 26.0 inches, which is sized for making three blocks with their upper faces on the pallet. The mold 52 comprises a plurality of generally identical block-forming cavities 56. Figure 7 illustrates five block-forming cavities 56 arranged side-by-side, which is possible when making the preferred size blocks on a standard "three-at-a-time" pallet. Of course, larger machines that use larger pallets are in use, and this technology can be used in both larger and smaller machines. The number of possible mold cavities in a single mold depends upon size of the machine and the size of the pallet. A plurality of block-forming cavities 56 allows increased production of blocks from the single mold 52.

With reference to Figure 7, the cavities 56 are formed by division plates 58, including a pair of outside division plates, a plurality of inside division plates, and a pair of end liners 60 that are common to each cavity 56. The use of outside and inside division plates and end liners to form a block-forming cavity in a

mold is known to those of skill in the art. The division plates and end liners form the boundaries of the block cavities and provide the surfaces that are in contact with the pre-cured blocks during block formation, and are thus susceptible to wear. Thus, the division plates and end liners are typically removably mounted within the mold
5 52 so that they can be replaced as they wear or if they become damaged. The techniques for mounting division plates and end liners in a mold to form block cavities, and to permit removal of the division plates and end liners, are known to those of skill in the art.

In the preferred embodiment, the division plates 58 form the upper
10 and lower faces 16, 18 of the blocks 10, while the end liners 60 form the side faces 20, 22. For convenience, the division plates and end liners will hereinafter (including in the claims) be referred to collectively as the side walls of the cavities. Thus, side walls refers to division plates and end liners, as well as to any other similar structure that is used to define the boundaries of a block-forming cavity.

Referring now to Figure 8, a portion of a single block-forming cavity
15 56 is illustrated. The cavity 56 defined by the side walls 58, 60 has an open top 64 and an open bottom 66. As shown, the top ends of the side walls 60 (e.g. the end liners) are connected by pivots 62 to suitable surrounding structure of the mold 52 to allow the side walls 60 to pivot between the closed position shown in Figure 8,
20 where the side walls 60 converge toward each other, to a retracted position where the side walls 60 are generally vertical and parallel to each other (not shown). In the retracted position, the bottom of the cavity 56 is at least as wide as the top of the mold cavity, which allows the pre-cured block to be discharged through the open bottom. When only a portion of either side face 20, 22 of the block converges, only
25 a corresponding portion of the side walls 60 will be pivoted. The side wall 58 that forms the lower face of the block 10 is also illustrated in Figure 8, while the other side wall 58 that forms the upper face of the block is not shown.

Pivoting of the side walls 60 is required in order to form the preferred
block 10. As discussed above, the block 10 is formed "face-up" in the mold 52 with
30 its converging side faces formed by the side walls 60. Thus, the converging side walls 60, when they are angled as illustrated in Figure 8, shape the converging side faces 20, 22 of the pre-cured block. However, the front portion of the pre-cured block is wider than the rear portion of the block. In order to be able to discharge the

pre-cured block through the open bottom 66, the side walls 60 must pivot outward to enable downward movement of the pre-cured block through the open bottom.

5 Biasing mechanisms 68 are provided to maintain the side walls 60 at the converging position during introduction of the concrete and subsequent compacting of the dry cast masonry concrete, and which allow the side walls 60 to pivot to a vertical position during discharge of the pre-cured block. Preferably, a single biasing mechanism 68 is connected to each side wall 60 that is common to all cavities 56, so that the movement of each side wall 60 is controlled via a common mechanism (see Figure 7). The biasing mechanisms 68 are illustrated as comprising
10 air bags, which will be controlled through the use of air or similar gas. Suitable inlet and outlet ports for the air will be provided, as will a source of high pressure air. The use of biasing mechanisms other than air bags is also possible. For example, hydraulic or pneumatic cylinders could be used.

 When pressurized with air, the air bags will force the side walls 60 to
15 the position shown in Figure 8. When it comes time to discharge the pre-cured block(s), the pressurized air is vented from the air bags, which allows the side walls 60 to pivot outward under force of the pre-cured block as the pre-cured block is discharged through the open bottom when the pallet is lowered. During block discharge, the side walls 60 remain in contact with the side faces of the pre-cured
20 block. Alternatively, biasing mechanisms, such as coil springs, can be connected to the side walls 60 to force the side walls to the retracted position when the air bags are vented. In this case, as the pallet 82 starts to lower to begin block discharging, the side walls 60 will be forced to the retracted position, and the side walls 60 will not contact the side faces of the block during discharge. After discharge, the side
25 walls 60 are returned to the closed, angled position by re-pressurizing the air bags.

 Rather than pivoting the side walls 60, it is possible to use other mechanisms to permit movement of the side walls 60 to allow discharge of the pre-cured block. For example, the side walls 60 could be mounted so as to slide inwards to the position shown in Figure 8 and outwards to a position where the bottom of the
30 cavity 56 is at least as wide as the top of the mold cavity. The sliding movements could be implemented using a track system in which the side walls are mounted.

 As shown in Figure 8, each side wall 60 includes a shaping surface 76 that faces the cavity 56. The shaping surfaces 76 are substantially planar. The result is the formation of substantially planar side faces 20, 22 of the block 10.

Referring now to Figure 9, the side walls 58 that form the upper and lower faces 16, 18 of the block 10 are illustrated. The side walls 58, which are fixed and not moveable during the molding process, are substantially vertical.

5 The side wall 58 that forms the upper face 16 (the left side wall 58 in Figure 9) includes a shaping surface 78 that faces the cavity 56. The surface 78 is substantially planar, which results in the formation of a substantially planar upper face 16.

10 The side wall 58 that forms the lower face 18 (the right side wall 58 in Figure 9) includes an undercut, or "instep", portion 80 at the bottom edge thereof adjacent the open bottom 66. The undercut portion 80, in combination with the pallet 82 that is introduced under the mold 52 to temporarily close the open mold bottom 66 during the molding process, defines a flange-forming subcavity of the cavity 56. The flange-forming subcavity has a shape that results in the formation of the flange 26 on the block 10.

15 In particular, the undercut portion 80 includes a shaping surface 84 that forms the front surface 28 of the flange 26, a shaping surface 86 that forms the bottom surface 30 of the flange, and a shaping surface 88 that forms the edge 32 of the flange 26. The portion of the flange 26 that is an extension of the rear face 14 is formed by and on the pallet 82, along with the remainder of the rear face 14. The shape of the surfaces 84 and 86 facilitate filling of the undercut portion 80 with the concrete during introduction and subsequent compacting of the concrete so that the flange 26 is completely formed, as well as aid in release of the flange 26 from the surfaces 84, 86 during block discharge.

20

In the case of a block having a flange on the lower face and no converging side faces, the side walls 60 would be oriented vertically instead of being converging. Further, in the case of a block without a flange on the lower face and with converging side faces, the undercut 80 would not be present. In the case of a block without a flange on the lower face and without converging side faces, the undercut 80 would not be present and the side walls 60 would be oriented vertically.

25

30 Returning to Figures 6 and 8, the head assembly 54 is seen to include a compression head 90 in the form of a plate. The head 90 is actuated by an actuating mechanism in a manner known in the art so that the head 90 is moveable vertically up and down to bring about compaction of the dry cast masonry concrete

in the mold cavities 56 and to assist in stripping the pre-cured blocks from the mold 52.

Connected to and extending from the bottom of the head 90 are a plurality of stand-offs 92, one stand-off for each block-forming cavity 56 as shown
5 in Figure 6. The stand-offs 92 are spaced from each other, with the longitudinal axis of each stand-off oriented perpendicular to the plane of the head 90 and extending generally centrally through the block-forming cavity 56.

A stripper shoe 94, illustrated in Figures 6, 8, 9 and 10, is connected to the end of each stand-off 92. The stripper shoe 94 is rectangular in shape and is
10 dimensioned so that it may enter the respective cavity 56 through the open top to contact the concrete to compact the concrete, and to travel through the cavity during discharge of the pre-cured block. The dimensions of the stripper shoe 94 are only slightly less than the dimensions of the open top 64 of the cavity 56, so that the shoe 94 fits into the cavity 56 with little or no spacing between the sides of the shoe 94
15 and the side walls 58, 60 defining the cavity. This minimizes escape of concrete between the sides of the shoe 94 and the side walls 58, 60 during compression, and maximizes the front face area of the block that is contacted by the shoe 94.

Flanges 98a, 98b are formed on opposite ends of the face of the stripper shoe 94, as best seen in Figure 10. The flanges 98a, 98b are arcuate to
20 produce the rounded edges 24a, 24b on front face 12 of the block. If desired, arcuate flanges can be provided on the two remaining ends of the stripper shoe 94, in order to produce upper and lower rounded edges on the front face 12.

As discussed above, a face of the shoe 94 is preferably provided with a pre-determined pattern 96 so that, as the shoe 94 compacts the concrete, the pattern
25 is imparted to the front face of the block. The pattern 96 preferably simulates natural stone, so that the front face of the resulting block simulates natural stone thereby making the block appear more natural and "rock-like". A variety of different patterns 96 can be provided on the shoe 94, depending upon the appearance of the front face that one wishes to achieve. In addition to, or separate from, the
30 pattern 96, the face of the shoe 94 can be shaped to achieve a faceted or curved block front face. Indeed, the face of the shoe 94 can be patterned and/or shaped in any manner which one desires in order to achieve a desired appearance of the block front face.

Figure 10 provides an example of a pre-determined pattern 96 that can be provided on the shoe 94. The pattern 96 simulates natural stone. The pattern 96 is preferably machined into the shoe face based upon a pre-determined three-dimensional pattern. An exemplary process for creating the pre-determined pattern 96 on the shoe face is as follows.

Initially, one or more natural rocks having surfaces which one considers to be visually pleasing are selected. One or more of the rock surfaces are then scanned using a digital scanning machine. An example of a suitable scanning machine for practicing the invention is the Laser Design Surveyor 1200 having an RPS 150 head, available from Laser Design Incorporated of Minneapolis, Minnesota. The Laser Design Surveyor 1200 has a linear accuracy of 0.0005" in the XYZ coordinates, and a resolution of 0.0001". The scan data for the rock surfaces is collected and manipulated to blend the scan data for each scanned surface together to create a seamless data blend of the various rock surfaces. The software for collecting and manipulating the scan data is known in the art, for example, DataSculpt available from Laser Design Incorporated of Minneapolis, Minnesota.

The data blend is then scaled and/or trimmed to the dimension of the block front face. The scaled data blend represents a single rock surface blended from the individually scanned rock surfaces. The scaled blend data is then output to a three or four axis, numerically controlled milling machine for milling of the stripper shoe 94. A suitable milling machine for practicing the invention is the Mikron VCP600 available from Mikron AG Nidau of Nidau, Switzerland. The milling machine mills a mirror image of the rock surface, represented by the scaled data blend, into the face of the stripper shoe 94, which is suitably mounted in the milling machine in known fashion. The result is a pre-determined pattern milled into the face of the shoe 94, which, in turn, results in a pre-determined pattern impressed into the front face of the block when the shoe 94 compacts the concrete.

This process can be repeated to produce additional shoes having the same or different face patterns. This is advantageous because the patterned face of each shoe is subject to wear, and the shoe will need to be replaced when the pattern becomes excessively worn. Further, by forming a variety of different pre-determined shoe patterns, a variety of different block front face appearances can be achieved. Other shoe patterns can be formed by combining the scanned surfaces of a plurality of different rocks.

As discussed above, the resulting detail and relief that is provided on the block front face can be significantly greater than the detail and relief that is provided on the front face of a block that results from conventional splitting techniques, and the other front face distressing techniques discussed above. If
5 desired, the scan data can be manipulated in order to increase or decrease the relief that is milled into the shoe face, which will alter the relief that is ultimately provided on the block front face.

It is known in the art that dry cast masonry concrete may have a tendency to stick to mold surfaces, such as the patterned surface of the stripper shoe
10 94. Various techniques to enhance the release of the stripper shoe 94 from the dry cast concrete are known, and one or more of them may need to be employed in the practice of this invention. For example, the pattern formed on the stripper shoe has to be designed to enhance, rather than inhibit, release. In this regard, appropriate draft angles have to be employed in the pattern. The pattern-forming techniques
15 described above permit manipulation of the scanned images to create appropriate draft angles. Release agents, such as a fine mist of oil, can be sprayed onto the stripper shoe between machine cycles. Head vibration can be employed to enhance release. And heat can be applied to the stripper shoe to enhance release. Heating mold components to prevent sticking of dry cast masonry concrete is known in the
20 art. In the present invention, due to the detailed pattern that is to be imparted to the block front face, it is even more important to prevent sticking. In particular, it is important to be able to control the temperature of the shoe so that the temperature can be maintained at selected levels.

Preferably, as shown diagrammatically in Figure 11, a heater 100 is
25 connected to the shoe 94 for heating the shoe. The heater 100 is controlled by a temperature control unit 102. A thermocouple 104 mounted on the shoe 94 senses the temperature of the shoe, and relays that information to a power control unit 106 that provides electrical power to the control unit 102 and the heater 100. The system is designed such that, when the temperature of the shoe 94 falls below a pre-
30 determined level as sensed by the thermocouple 104, power is provided to the heater 100 to increase the shoe temperature. When the shoe temperature reaches a pre-determined level, as sensed by the thermocouple, the heater 100 is shut off. Thus, the shoe temperature can be maintained as selected levels. Preferably, the control unit 102 is designed to allow selection of the minimum and maximum temperature

levels, based on the dry cast masonry concrete that is being used. In the preferred embodiment, the surface temperature of the stripper shoe 94 is maintained between 120 °F and 130 °F.

- The above specification, examples and data provide a complete
- 5 description of the manufacture and use of the composition of the invention. Since many embodiments of the invention can be made without departing from the spirit and scope of the invention, the invention resides in the claims hereinafter appended.

WHAT IS CLAIMED IS:

1. A process for producing a masonry block having upper and lower faces, a front face, a rear face, opposed side faces, and an integral flange
5 extending below the lower face of the block, the method comprising the steps of:
providing a mold having a plurality of side walls defining a mold cavity with an open top and an open bottom, a first side wall having an undercut portion adjacent the open bottom of the mold cavity;
positioning a pallet underneath the mold to temporarily close the
10 open bottom of the mold cavity, whereby the pallet cooperates with the undercut portion of the first side wall to define a flange-forming subcavity of the mold cavity;
introducing dry cast masonry concrete into the mold cavity through the open mold top;
compacting the dry cast masonry concrete to form a pre-cured
15 masonry block with the rear face of the block resting on the pallet and the front face of the block facing upward;
reopening the temporarily-closed bottom of the mold cavity;
discharging the pre-cured masonry block from the mold cavity through the reopened bottom of the mold cavity; and
20 curing the pre-cured masonry block.
2. A masonry block produced by the process of claim 1.
3. The process of claim 1, which further includes the steps,
25 following the introduction of dry cast masonry concrete into the mold cavity, of introducing a stripper shoe having a face that comprises a three-dimensional pattern into the mold cavity through the open top of the mold cavity, and pressing the patterned face of the stripper shoe on the dry cast masonry concrete contained in the mold cavity, to impart a pattern to the front face of the pre-cured masonry block.
30
4. A masonry block produced by the process of claim 3.
5. The process of claim 3, wherein the pattern of the face of the stripper shoe simulates natural stone.

6. A masonry block produced by the process of claim 5.

7. The process of claim 5, wherein said compacting step
5 includes vibrating the concrete contained in the mold cavity.

8. The process of claim 1, wherein a second side wall of the
mold, which is generally perpendicular to said first side wall, includes a first
converging side wall portion that is, immediately prior to the concrete-introducing
10 step, oriented at an angle with respect to vertical, so that the mold cavity is wider at
its top than it is at its bottom during the concrete-introducing and compacting steps,
and wherein the first converging side wall portion of the mold is moveably mounted,
and there is included the step of moving the first converging side wall portion to a
position in which the bottom of the mold cavity is at least as wide as the top of the
15 mold cavity to allow the pre-cured masonry block to be discharged through the
reopened bottom of the mold cavity.

9. A masonry block produced by the process of claim 8.

10. The process of claim 8, wherein the side wall of the mold that
20 is opposite the second side wall includes a second converging side wall portion
which is opposite the first converging side wall portion, and wherein the second
converging side wall portion is, immediately prior to the concrete-introducing step,
oriented at an angle with respect to vertical, so that the mold cavity is wider at its top
25 than it is at its bottom during the concrete-introducing and compacting steps, and
wherein the second converging side wall portion is moveably mounted, and there is
included the step of moving the second converging side wall portion to a position in
which the bottom of the mold cavity is at least as wide as the top of the mold cavity
30 to allow the pre-cured masonry block to be discharged through the reopened bottom
of the mold cavity.

11. The process of claim 10, wherein the first and second
converging portions of the side walls of the mold are biased to their pre-concrete

introduction angled orientations by bias forces, and wherein the bias forces are released to permit the pre-cured masonry block to be discharged from the mold.

12. The process of claim 11, wherein the bias forces are provided
5 by air bags.

13. The process of claim 1, wherein the temporarily closed
bottom of the mold cavity is reopened, and the pre-cured masonry block is
discharged through the open bottom of the mold cavity by lowering the pallet
10 relative to the mold.

14. The process of claim 1 wherein said mold includes a plurality
of said mold cavities which operate with a single pallet to mold a plurality of blocks
at the same time.

15
15. A process for producing a masonry block having upper and
lower faces, a patterned front face, a rear face and opposed side faces, a first of said
side faces having a first converging portion that converges towards said second side
face as the side faces extend toward said rear face, the method comprising the steps
20 of:

providing a mold having a plurality of side walls defining a mold
cavity with an open top and an open bottom, one side wall of the mold including a
first converging side wall portion that is oriented at an angle with respect to vertical,
so that the mold cavity is wider at its top than it is at its bottom;

25 positioning a pallet underneath the mold to temporarily close the
open bottom of the mold cavity, whereby the pallet cooperates with the undercut
portion of the first side wall to define a flange-forming subcavity of the mold cavity;

introducing dry cast masonry concrete into the mold cavity through
the open mold top;

30 compacting the dry cast masonry concrete to form a pre-cured
masonry block with the rear face of the block resting on the pallet and the front face
of the block facing upward, said compacting step including introducing a stripper
shoe having a face that comprises a three-dimensional pattern into the mold cavity
through the open top of the mold cavity, and pressing the patterned face of the

- stripper shoe on the dry cast masonry concrete contained in the mold cavity, to impart a pattern to the front face of the pre-cured masonry block;
reopening the temporarily-closed bottom of the mold cavity;
moving the first converging side wall portion of the mold to a
5 position in which the bottom of the mold cavity is at least as wide as the top of the mold cavity to allow the pre-cured masonry block to be discharged through the reopened bottom of the mold cavity;
discharging the pre-cured masonry block from the mold cavity
through the reopened bottom of the mold cavity; and
10 curing the pre-cured masonry block.
16. A masonry block produced by the process of claim 15.
17. The process of claim 16, wherein said compacting step
15 includes vibrating the concrete contained in the mold cavity.
18. The process of claim 15, wherein the side wall of the mold opposite said one side wall includes a second converging side wall portion which is opposite the first converging side wall portion, and wherein the second converging
20 side wall portion is, immediately prior to the concrete-introducing step, oriented at an angle with respect to vertical so that the mold cavity is wider at its top than it is at its bottom during the concrete-introducing and compacting steps, and wherein the second converging side wall portion is moveably mounted, and including the step of moving said second converging wall portion to a position in which the bottom of the
25 mold cavity is at least as wide as the top of the mold cavity to allow the pre-cured masonry block to be discharged through the reopened bottom of the mold cavity.
19. A masonry block produced by the process of claim 18.
20. The process of claim 18, wherein the first and second
30 converging portions of the side walls of the mold are biased to their pre-concrete introduction angled orientations by bias forces, and wherein the bias forces are released to permit the pre-cured masonry block to be discharged from the mold.

21. The process of claim 20, wherein the bias forces are provided by air bags.

22. The process of claim 15, wherein the temporarily closed
5 bottom of the mold cavity is reopened, and the pre-cured masonry block is discharged through the open bottom of the mold cavity by lowering the pallet relative to the mold.

23. The process of claim 15 wherein said mold includes a
10 plurality of mold cavities which operate with a single pallet to mold a plurality of blocks at the same time.

24. A mold assembly for use in forming a pre-cured dry cast masonry block having upper and lower faces, a front face, a rear face, opposed side
15 faces, and an integral flange extending below the lower face of the block, the mold assembly comprising:

a plurality of side walls defining a mold cavity having an open mold top and an open mold bottom, a first of said side walls including an undercut adjacent the open mold bottom that, along with a pallet that closes the bottom of the
20 mold, defines a flange-forming subcavity of the mold cavity.

25. The mold assembly of claim 24 including a stripper shoe having a face that comprises a three-dimensional pattern for introduction into the mold cavity through the open top of the mold cavity to press the patterned face of
25 the stripper shoe on dry cast masonry concrete contained in the mold cavity, to impart a pattern to the front face of a pre-cured masonry block

26. The mold assembly of claim 25 wherein the pattern of the face of the stripper shoe simulates natural stone.
30

27. The mold assembly of claim 26, wherein said stripper shoe includes a flange surrounding the perimeter of the patterned face and said flange is arcuate so as to produce rounded edges on the front face of the masonry block.

28. The mold assembly of claim 24, wherein the remainder of said side wall with said undercut is substantially planar and extends substantially vertically.

5 29. The mold assembly of claim 24, wherein a second side wall of the mold, which is generally perpendicular to said first side wall, includes a first converging side wall portion that is moveably mounted so that it is movable between a position at an angle with respect to vertical so that the mold cavity is wider at its top than it is at its bottom when dry cast masonry concrete is introduced into the
10 mold cavity, and a position in which the bottom of the mold cavity is at least as wide as the top of the mold cavity to allow the pre-cured masonry block to be discharged through the bottom of the mold cavity.

30. The mold assembly of claim 29 wherein the side wall of the
15 mold opposite said second side wall includes a second converging side wall portion which is opposite the first converging side wall portion, and wherein the second converging side wall portion is moveably mounted so that it is movable between a position at an angle with respect to vertical so that the mold cavity is wider at its top than it is at its bottom when dry cast masonry concrete is introduced into the mold
20 cavity, and a position in which the bottom of the mold cavity is at least as wide as the top of the mold cavity to allow the pre-cured masonry block to be discharged through the bottom of the mold cavity.

31. The mold assembly of claim 30, wherein said converging side
25 wall portions are pivoted near ends thereof adjacent the open mold top.

32. The mold assembly of claim 30, further including a
mechanism for biasing each of said converging side wall portions to the angled
position.

30

33. The mold assembly of claim 32, wherein the mechanism for biasing each of said converging side wall portions comprises an air bag connected to each converging side wall portion.

34. The mold assembly of claim 30, wherein each of said converging side wall portions includes a substantially planar surface facing the mold cavity.

5 35. The mold assembly of claim 24 comprising a plurality of said mold cavities which operate with a single pallet to mold a plurality of blocks at the same time

36. A mold assembly for use in forming a pre-cured dry cast
10 masonry block having upper and lower faces, a front face, a rear face, opposed side faces, and an integral flange extending below the lower face of the block, the mold assembly comprising:

a plurality of side walls defining a mold cavity having an open mold top and an open mold bottom, a first of said side walls of the mold includes a first
15 converging side wall portion that is moveably mounted so that it is movable between a position at an angle with respect to vertical so that the mold cavity is wider at its top than it is at its bottom when dry cast masonry concrete is introduced into the mold cavity, and a position in which the bottom of the mold cavity is at least as wide as the top of the mold cavity to allow the pre-cured masonry block to be discharged
20 through the bottom of the mold cavity; and

a stripper shoe having a face that comprises a three-dimensional pattern for introduction into the mold cavity through the open top of the mold cavity to press the patterned face of the stripper shoe on dry cast masonry concrete contained in the mold cavity, to impart a pattern to the front face of a pre-cured
25 masonry block.

37. The mold assembly of claim 36 wherein the pattern of the face of the stripper shoe simulates natural stone.

30 38. The mold assembly of claim 37, wherein said stripper shoe includes a flange surrounding the perimeter of the patterned face and said flange is arcuate so as to produce rounded edges on the front face of the masonry block.

39. The mold assembly of claim 36 wherein the side wall of the mold opposite said one side wall includes a second converging side wall portion which is opposite the first converging side wall portion, and wherein the second converging side wall portion is moveably mounted so that it is movable between a position at an angle with respect to vertical so that the mold cavity is wider at its top than it is at its bottom when dry cast masonry concrete is introduced into the mold cavity, and a position in which the bottom of the mold cavity is at least as wide as the top of the mold cavity to allow the pre-cured masonry block to be discharged through the bottom of the mold cavity.

10

40. The mold assembly of claim 39, wherein said converging side wall portions are pivoted near ends thereof adjacent the open mold top.

41. The mold assembly of claim 39, further including a mechanism for biasing each of said converging side wall portions to the angled position.

15

42. The mold assembly of claim 41, wherein the mechanism for biasing each of said converging side wall portions comprises an air bag connected to each converging side wall portion.

20

43. The mold assembly of claim 39, wherein each of said converging side wall portions includes a substantially planar surface facing the mold cavity.

25

44. The mold assembly of claim 36 comprising a plurality of said mold cavities which operate with a single pallet to mold a plurality of blocks at the same time

30

45. A mass produced dry cast concrete masonry block suitable for use in building soil retaining walls, comprising:
an upper face;

a lower face suitable for engaging said upper face of an adjacent block to maintain a generally parallel relationship between the upper faces of blocks in successive courses of blocks when the blocks are stacked together to form a wall;

a patterned front face that joins said upper and lower faces, the
5 pattern having been imparted to the front face of the block during the molding process by the action of a moveable stripper shoe having a mirror image of the patterned front face;

a rear face;

a first generally vertical side face joining said front and rear faces;

10 a second generally vertical side face opposed to the first side face and joining said front and rear faces; and

a flange extending below said lower face of the block to provide a surface suitable for engaging the block with the rear face of a different block in the course below said block to thereby provide a pre-determined set-back to a retaining
15 wall constructed from such block.

46. The masonry block of claim 45, wherein a first converging portion of said first side face converges towards said second side face as the side faces extend toward said rear face, and wherein said first converging portion is
20 formed by a moveable mold surface during the molding process.

47. The masonry block of claim 46 further including a second converging portion of said second side face, that converges towards said first side face as the side faces extend toward said rear face, and wherein said second
25 converging portion is formed by a moveable mold surface during the molding process.

48. The masonry block of claim 45 wherein the front face of the block is generally vertical.
30

49. The masonry block of claim 45 wherein the front face is oriented so that its upper edge where it intersects the upper face of the block is closer to the rear face of the block than is its lower edge where it intersects the lower face of the block.

50. The masonry block of claim 48 wherein the upper edge of the front face is closer to the rear face of the block than is its lower edge by a distance which is approximately equal to the pre-determined set back.

5

51. The masonry block of claim 45, wherein at least a portion of each side face is textured during the molding process.

52. The masonry block of claim 45, wherein said patterned front
10 face of said block has a relief of at least 0.5 inches.

53. A mass produced dry cast concrete masonry block suitable for use in building soil retaining walls, comprising:

an upper face;

15 a lower face suitable for engaging said upper face of an adjacent block to maintain a generally parallel relationship between the upper faces of blocks in successive courses of blocks when the blocks are stacked together to form a wall;

a patterned front face that joins said upper and lower faces, the pattern having been imparted to the front face of the block during the molding
20 process by the action of a moveable stripper shoe having a mirror image of the patterned front face;

a rear face;

a first generally vertical side face joining said front and rear faces;

a second generally vertical side face opposed to the first side face and
25 joining said front and rear faces; and

wherein a first converging portion of said first side face converges towards said second side face as the side faces extend toward said rear face, and wherein said first converging portion is formed by a moveable mold surface during the molding process.

30

54. The masonry block of claim 53 further including a second converging portion of said second side face opposite said first converging portion of said first side face, said second converging portion converging towards said first side face as the side faces extend toward said rear face, and wherein said second

converging portion is formed by a moveable mold surface during the molding process.

55. The masonry block of claim 53 wherein the front face of the
5 block is generally vertical.

56. The masonry block of claim 53 wherein the front face is oriented so that its upper edge where it intersects the upper face of the block is closer to the rear face of the block than is its lower edge where it intersects the lower
10 face of the block.

57. The masonry block of claim 55 wherein the upper edge of the front face is closer to the rear face of the block than is its lower edge by a distance which is approximately equal to the pre-determined set back.

15

58. The masonry block of claim 53, wherein at least a portion of each side face is textured during the molding process.

59. The masonry block of claim 53, wherein said patterned front
20 face of said block has a relief of at least 0.5 inches.







FIG. 4





FIG. 5






FIG. 6




FIG. 7




FIG. 9




FIG. 10





FIG. 11






FIG. 12A




FIG. 12B




FIG. 12C

INTERNATIONAL SEARCH REPORT

PCT/US 02/41543

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 E04C1/39 B28B7/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B28B E04C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 100 02 390 A (SF KOOP GMBH BETON KONZEPTE) 26 July 2001 (2001-07-26)	1-4, 13, 14, 24, 25, 27, 28, 45, 48-50 15, 36
A	column 4, line 44 - column 5, line 13 column 5, line 21 - line 31 claims 10, 11; figures 2, 3, 11	
X	US 5 827 015 A (SIEVERT DICK J ET AL) 27 October 1998 (1998-10-27) cited in the application column 4, line 12 - line 39; figure 1 -/--	45-48, 53-55



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

16 April 2003

Date of mailing of the international search report

28/04/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ortj, J

INTERNATIONAL SEARCH REPORT

PCT/US 02/41543

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 196 34 499 A (HERMANN KUESEL GMBH) 5 March 1998 (1998-03-05) the whole document	1,2, 8-16, 18-24, 29-36, 39-44
A	GB 2 232 114 A (BORAL EDENHALL CONCRETE PRODUC) 5 December 1990 (1990-12-05) page 9, last paragraph -page 10, paragraph 1; figures 6,7	1,5-13
A	US 3 694 128 A (FOXEN BENJAMIN F) 26 September 1972 (1972-09-26) the whole document	1,8-13

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

PCT/US 02/41543

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
DE 10002390	A	26-07-2001	DE	10002390 A1		26-07-2001
			AU	2513401 A		31-07-2001
			WO	0153612 A1		26-07-2001
<hr/>						
US 5827015	A	27-10-1998	US	5589124 A		31-12-1996
			US	5294216 A		15-03-1994
			US	5062610 A		05-11-1991
			US	6142713 A		07-11-2000
			US	6183168 B1		06-02-2001
			US	6312197 B1		06-11-2001
			US	2002015620 A1		07-02-2002
			AU	684211 B2		04-12-1997
			AU	3042295 A		30-11-1995
			AU	3542093 A		03-06-1993
			AU	638554 B2		01-07-1993
			AU	7263191 A		12-12-1991
			CA	2019033 A1		07-12-1991
<hr/>						
DE 19634499	A	05-03-1998	DE	19634499 A1		05-03-1998
<hr/>						
GB 2232114	A	05-12-1990	NONE			
<hr/>						
US 3694128	A	26-09-1972	NONE			

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)